



➤ PRODUCTS | PETROLEUM PRODUCTS | BITUMEN GRADE 60/70

We supply bitumen in bulk, drums and polycubes with different penetration grades.

Bitumen Grade 60/70		
PARAMETERS	SPECIFICATION	TEST METHOD
Specific gravity @25/25 C	1.01-1.06	D-70
Penetration @25 C	60/70	D-5
Softening point C	49/56	D-36
Ductility @25 C	100 min	D-113
Loss on heating (Wt)%	0.2 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point C	250min	D-92
Solubility in CS ₂ (Wt)%	99.5 min	D-4
Spot test	negative	*A.A.S.H.O.T.102

