



➤ PRODUCTS | PETROLEUM PRODUCTS | BITUMEN GRADE 80/100

We supply bitumen in bulk, drums and polycubes with different penetration grades.

Bitumen Grade 80/100		
PARAMETERS	SPECIFICATION	TEST METHOD
Specific gravity @25/25 C	1.00-1.05	D-70
Penetration @25 C	85/100	D-5
Softening point C	45/52	D-36
Ductility @25 C	100 min	D-113
Loss on heating (wt)%	0.5 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point C	250 min	D-92
Solubility in CS ₂ (wt)%	99.5 min	D-4
Organic matter insoluble in CS ₂ (wt)%	0.2 max	D-4
Spot test	negative	*A.A.S.H.O.T.102

Packing 1: In corrugated newly produced cold rolled steel drums coated in black / 20FT Containers / 110 drums per 20FT container

Packing 2: In poly cube with net weight of 300 kgs per bag/ 80 poly cubes per 20FT container

